

DIRECTIONS FOR USE

SURFACE PREPARATION: New concrete should be allowed to cure for a minimum of 28 days before coating. The concrete must be structurally sound, free of loose or deteriorated concrete and free of dust, dirt, paint, efflorescence, oil and other contaminants. Mechanically abrade the surface to achieve a surface profile equal to CSP 2-4 in accordance with ICRI Guideline 310.2. Properly clean profiled area. The pH of the surface should be checked per ASTM D 4262. Following surface preparation, the cleaned surface should have a minimum surface tensile strength of 200 psi (1.4 MPa) when tested with an Elcometer or similar pull tester (ASTM D 4541). Before application of the epoxy, use the "Visqueen test" (ASTM D 4263) or "Calcium Chloride Test" (ASTM F 1869) to evaluate the moisture level in the concrete. Do not proceed if a moisture vapor drive condition exists. Moisture vapor emission rate may vary over time depending upon environmental conditions. All steel surfaces should be blasted in accordance with SSPC-SO10 or NACE #2 to a "NEAR WHITE" finish using clean, dry blasting media.

MIXING: Pre-mix Part A and Part B, then combine 2 parts by volume of Part A with one part by volume of Part B and thoroughly mix using a low speed drill motor and a "Jiffy" type mixer. Mix only the amount of material that can be applied during the pot life. Do not aerate the mix.

APPLICATION: See the "Application Guide for Euclid Chemical Decorative and Industrial floor Coatings" for complete instructions.

CLEAN-UP

Clean tools and application equipment with SOLV-KLEEN, methyl ethyl ketone or acetone immediately after use. Clean spills or drips with solvent while still wet. Dried HIGH PERFORMANCE EPOXY will require mechanical abrasion for removal.

PRECAUTIONS/LIMITATIONS

- Store at temperatures between 50 to 90 °F (10 to 32 °C).
- Do not aerate during mixing.
- Do not mix or apply unless surface, air, and material temperatures are 50 °F (10 °C) and rising.
- Do not apply if surface temperature is within 5 °F (-15 °C) of the dew point in the work area.
- Cure new concrete 28 days before application.
- Do not apply to slabs on grade unless a heavy uninterrupted vapor barrier has been installed under the slab.
- Do not apply if the floor is subject to moisture vapor drive or hydrostatic pressure.
- HIGH PERFORMANCE EPOXY will yellow upon prolonged exposure to sunlight or high intensity artificial lights. For applications requiring color stability, urethane should be used as a topcoat.
- Although epoxy coatings are chemically resistant, the surface may stain after contact with some chemicals. A urethane topcoat is recommended for improved stain resistance.
- For professional use only.
- In all cases, consult the Safety Data Sheet before use.

Rev. 09.15

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.