# SINGLE COMPONENT SPRAY-DECK GROUT



# POLYMER-MODIFIED CEMENTITIOUS COATING

#### **DESCRIPTION**

**SINGLE-COMPONENT SPRAY-DECK GROUT** is a pre-blended cementitious coating, and is an ideal horizontal or vertical cover-up for unsightly existing concrete and masonry. SINGLE-COMPONENT SPRAY-DECK GROUT is uniquely formulated with fine aggregate that transforms concrete or masonry substrates into a non-slip, textured surface.

# **PRIMARY APPLICATIONS**

- Pool decks
- · Shopping centers
- Walkways
- Residential and commercial entrances

- Patio decks
- Plazas
- Showroom floors
- · Vertical applications

## **FEATURES**

- · One component, easy to mix and use
- Durable, wear-resistant
- · May be integrally colored

- Interior or exterior use
- Trowel, squeegee or spray apply

## **PACKAGING**

SINGLE-COMPONENT SPRAY-DECK GROUT is available in a 50 lb (22.7 kg) bag.

# SHELF LIFE

1 Year in original, unopened packaging.

# COVERAGE

One bag of SINGLE COMPONENT SPRAY-DECK GROUT will cover 150 ft<sup>2</sup> (13.9 m<sup>2</sup>) for a skim coat, 75 ft<sup>2</sup> (6.96 m<sup>2</sup>) for a final coat. The average coverage can vary greatly depending upon the application process and the porosity of the surface. A test area is recommended to determine coverage rate and project requirements.

## **DIRECTIONS FOR USE**

For complete detailed instructions, consult SPRAY-DECK/TEXTURE-CRETE Installation Instructions.

#### **APPLICATION PROCESS**

**Surface Preparation:** Concrete surfaces must be structurally sound, free of loose or deteriorated concrete and free of dust, dirt, paint, efflorescence, oil and other contaminants. Mechanically abrade the surface to achieve a surface profile equal to CSP 4-6 in accordance with ICRI Guideline 310.2. Properly clean profiled area.

**Mixing:** Add 4 to 6 qt (3.8 to 5.4 L) of clean, potable, cold water to a clean 5 gal (18.9 L) pail plastic pail. Begin mixing while slowly adding one 50 lb (22.7 kg) bag of SINGLE-COMPONENT SPRAY-DECK GROUT. Continue mixing for 2 to 3 minutes.

**Application:** The grout can then be troweled, squeegeed, or sprayed on the surface at a thickness not to exceed 1/4 in (6.35 mm).

**Seal:** After at least 24 hours drying time, the surface must be scraped, broomed, and blown with a high velocity blower and then sealed with CLEAR SEAL or CONCRETE STAIN SEALER. SHUR-GRIP may be added to the sealer for additional slip resistance.

#### **MAINTENANCE**

Sweep surface as necessary. Wash surface with a mild soap/detergent and rinse with water. Use GREASE-AWAY as needed.

# PRECAUTIONS/LIMITATIONS

- · Protect surrounding areas and surfaces from overspray.
- · For professional use only.
- In all cases, consult the Safety Data Sheet before use.