



High Quality Decorative Protective Sealers.

ACRATHANE COLORSEAL/CLEARSEAL

COLORSEAL APPLICATION

Multicoat COLORSEAL must be applied in two coats.

First Coat: Mix COLORSEAL to uniformity with slow speed mixer. With continuous mixing add clean water in ratio of 1 part water to 3 parts COLORSEAL. Apply diluted COLORSEAL with nap roller with very firm pressure. (1/2" nap roller for smooth and 3/4" nap roller for rough surfaces). Allow a minimum of one (1) hour to dry.

Second Coat: Mix to uniformity only. Apply with firm pressure. DO NOT APPLY THICKER THAN RECOMMENDED. Airless sprayers may be used for the final coat. Allow final coat a minimum of 24 hours before placing area into use. Will fully cure in 14 days, during which care should be exercised against excessive abuse. **Each pail has a 'lot' number. Do not mix lot numbers during the final coat. If more than one lot number must be used, box the material to insure color uniformity.**

CLEARSEAL APPLICATION

Mix to uniformity with slow speed mixer. DO NOT DILUTE CLEARSEAL, use as packaged. One coat application is recommended for a semi-gloss appearance. Two coats will have a shiny gloss appearance. Clear Seal goes on white and dries clear.

LIMITATIONS

Do not apply if substrate temperature is below 40°F or above 100°F, or if ambient temperature below 40°F above 100°F.

Do not apply if precipitation is expected within a twenty four (24) hour period.

COVERAGE

ACRATHANE COLORSEAL and CLEARSEAL: 200 - 300 sq. ft. per gallon depending on surface texture, porosity and method of application.



ONE GALLON CANS
FIVE GALLON PAILS

PACKAGING AND STORAGE

COLORSEAL and CLEARSEAL: Furnished in 1 gallon cans and 5 gallon Pails. Shelf life approximately 18 months in unopened containers. Store at 40° to 90° F in a dry environment.

DAMAGE LIMITATION

Seller shall not be liable for any damages, injury, loss, direct or consequential, resulting from its products. The parties intend that the limitation of damages, including consequential damages, applies even if the exclusive remedy provided for herein fails of its essential purpose.

EXCLUSIVE REMEDY

Seller's sole obligation, and buyer's exclusive remedy shall be to replace material if found to be defective.

WARRANTY DISCLAIMER

There are no warranties which extend beyond the description of the fact hereof. Seller expressly disclaims all other warranties regarding the use of its products, whether expressed or implied, including the implied warranties of merchantability and for fitness of a particular purpose. Since use of the product is beyond the Seller's control, the Buyer assumes all risk of use.

WARRANTY

Materials are guaranteed with respect to uniformity and quality within manufacturer's specifications.

TEST DATA - ACRATHANE COLORSEAL/CLEARSEAL

TEST	METHOD	RESULTS
1. Chemical Resistance Test	ASTM D2299	
	Turpentine	1
	Gasoline	1
	Paint Thinner	1
	Lubricating Oil	1
	Sulfuric Acid—3%	2
	Hydraulic Fluids	3
	Toluene	1
	Salt Solution 20%	1
	Muratic Acid 10%	1
	Prestone Coolant	1

TEST RESULTS KEY

- 1. Unaffected
- 2. Superficial Affect (Will need to be cleaned.)
- 3. Considerable Affect (May have to re-seal)



MULTICOAT® CORPORATION

West Coast

Toll Free: (877) 685-8426
(949) 888-7100 Fax (949) 888-2555
Website: www.multicoat.com
E-mail: info@multicoat.com

MULTICOAT® PRODUCTS, INC.

East Coast

Toll Free: (800) 660-6729
(304) 586-0616 Fax (304) 586-0620
Website: www.multicoat.com
E-mail: info@multicoat.com

AVAILABLE THROUGH



MC311

The Coating of the Future...Today

MC311